

SELENIZZA COL® AS03 Technical Data Sheet

SELENIZZA COL® AS03

Specifications	Method	Min Value	Max Value	Typical Value ±2%
Penetration at 25°C (1/10mm)	EN 1426	0.80	1.20	1
Softening Point (°C)	ASTM E28-92	165	180	174
Moisture (%)	ASTM D3302	-----	2.00	1.07
Specific Gravity	ASTM D3289	1.00	1.05	1.02
Ash (%)	ASTM D3174	-----	2.00	1.16
Solubility in TCE (%)	ASTM D3175	97.00	100.00	98.81
Total Asphaltenes (%)	IP 469	85.00	92.00	88.50
* Polar Resin % Included	IP 469	40.00	42.00	41.50

Packaging

It is available in 650 kg, 1,250 kg or 1,400 kg big bag (no pallet) or 15 kg bags which are stretch wrapped and palletized.

Mesh

Our SELENIZZA COL® AS03 can be delivered on mesh 05, 20, 50 and 100.